


GLOBAL OPTICS (UK) LTD

30 Brockley Road, Bournemouth
Dorset, BH10 6JN.
Tel: 01202 530609
Fax: 01202 547209
Email: globalopticsuk@btinternet.com
Website: www.globalopticsuk.co.uk

ZINC SULPHIDE - Regular Grade

Used for Infrared windows and lenses. The Regular (FLIR) grade is visibly opaque and the Multispectral grade is the water clear form for visible and infrared applications.

Transmission Range	0.3 - 14.0 μ
Crystal Structure	Polycrystalline Cubic
Cleavage Plane	None
Colour	Opaque
Density	4.09
Melting Point ($^{\circ}$)	-
Reflection Loss	-
Solubility index	65×10^{-6} /100gm water
Hardness (Knoop)	210-240kg/mm ²
Thermal Conductivity (cal/cm sec $^{\circ}$ C)	0.16 (W/cm $^{\circ}$ C)
Thermal Expansion coefficient (/ $^{\circ}$ C)	6.8×10^{-6} / $^{\circ}$ K



Whilst every effort has been made to verify the data provided, no responsibility can be accepted for its accuracy